

**Richtrezeptur Nr. 1. 5238 - 02**

**KH - Malerweißlack**  
**VOC < 300 g/l (2010)**  
**Kategorie A / d**

<b>WorléeKyd SD 7003</b>	85%ig in entaromat. KW 160-200	50,50
<b>WorléeThix 670 hs</b>	70%ig in entaromat. KW 160-200	5,00
Disperbyk 107		0,20 (Byk)
<b>Permablend VPA 307</b>		0,05 (MK-Chemicals/Worlée)
Kronos 2315		30,00 (Kronos)
Entaromat. KW 160-200		11,05
OS-Kobalt 6		0,45 (Borchers)
OS-Calcium 10		0,70 (Borchers)
OS-Zirkonium 12		0,55 (Borchers)
<b>WorléeAdd 373 N</b>		1,00
Borchi Nox M2		0,50 (Borchers)
		<u>100,00</u>

Nichtflüchtiger Anteil: ca. 76,5%  
Dichte, 20 °C: ca. 1,21 g/cm<sup>3</sup>  
**VOC - Gehalt: ca. 285 g/l**

**Worlée - Chemie G.m.b.H.**  
ATA - 1 -  
Stand : Februar 2009