

Richtrezeptur Nr. 1. 5238 - 04

KH - Seidenglanzlack, weiß
VOC < 300 g/l (2010)
Kategorie A / d

WorléeKyd SD 7003	85%ig in entaromat. KW 160-200	34,30	
WorléeThix 670 hs	70%ig in entaromat. KW 160-200	9,00	
Disperbyk 107		0,20	(Byk)
Permablend VPA 307		0,05	(MK-Chemicals/Worlée)
Kronos 2310		28,00	(Kronos)
Heladol 30		11,00	(Herbert Lange)
Köstropur 050818		4,00	(CWK /Worlée)
Entaromat. KW 160-200		5,10	
Entaromat. KW 180-220		5,00	
WorléeAdd 429		1,50	
OS-Kobalt 6		0,35	(Borchers)
OS-Calcium 10		0,55	(Borchers)
OS-Zirkonium 12		0,45	(Borchers)
Borchi Nox M2		0,50	(Borchers)
		<u>100,00</u>	

Nichtflüchtiger Anteil: ca. 78,5%
Dichte, 20 °C: ca. 1,35 g/cm³
VOC - Gehalt: ca. 290 g/l

Worlée - Chemie G.m.b.H.
ATA - 1 -
Stand: März 2009