

Richtrezeptur Nr. 1.5238 - 08

KH - Vorlack, weiß
VOC < 300 g/l (2010)
Kategorie A / d

WorléeKyd SD 7003	85%ig in entaromat. KW 160-200	20,00
WorléeThix 670 hs	70%ig in entaromat. KW 160-200	5,00
Disperbyk 107		0,20 (Byk)
Kronos 2315		23,00 (Kronos)
Heladol 30		32,50 (Herbert Lange)
Sipernat 820 A		6,00 (Degussa)
Entaromat. KW 160-200		11,78
OS-Kobalt 6		0,17 (Borchers)
OS-Calcium 10		0,35 (Borchers)
OS-Zirkonium 12		0,50 (Borchers)
Borchi Nox M2		0,50 (Borchers)
		<u>100,00</u>

Nichtflüchtiger Anteil: ca. 82,0%
Dichte, 20 °C ca. 1,60 g/cm³
VOC - Gehalt: ca. 290 g/l

Worlée - Chemie G.m.b.H.
ATA - 1 -
Stand: Februar 2009