

Starting Point Formulation No. 1.5267 - 06

Primer paint, white
VOC < 300 g/l (2010)
Category A / d

WorléeKyd SD 7003	85% in dearomat. HC 160-200	21.30
Resiflow LH 240	approx. 100%	1.00
WorléeAdd 810 paste	10% in dearomat. HC 160-200	4.00
Disperbyk 107		0.20 (Byk)
Kronos 2310		20.00 (Kronos)
Bayoxide Z aktiv		1.00 (Lanxess)
Finntalc M 15		7.50 (Omya)
Micro Mica W 1		7.50 (Omya)
Heladol 30		25.50 (Herbert Lange)
Dearomat. HC 160-200		10.70
OS-Cobalt 6		0.20 (Borchers)
OS-Calcium 10		0.35 (Borchers)
OS-Zirconium 12		0.25 (Borchers)
Borchi Nox M2		0.50 (Borchers)
		<u>100.00</u>

Viscosity DIN 53211-6, 20 °C: approx. 59 s
 Non volatile part: approx. 82.0%
 Density, 20 °C approx. 1.61 g/cm³
VOC - content: approx. 290 g/l

Worlée - Chemie G.m.b.H.
 ATA - 1 -
 Revision: September 2009