

Starting Point Formulation No. 1. 5238 - 04

Silk gloss paint, white
VOC < 300 g/l (2010)
Category A / d

WorléeKyd SD 7003	85% in dearomat. HC 160-200	34.30	
WorléeThix 670 hs	70% in dearomat. HC 160-200	9.00	
Disperbyk 107		0.20	(Byk)
Permablend VPA 307		0.05	(MK-Chemicals/Worlée)
Kronos 2310		28.00	(Kronos)
Heladol 30		11.00	(Herbert Lange)
Köstropur 050818		4.00	(CWK /Worlée)
Dearomat. HC 160-200		5.10	
Dearomat. HC 180-220		5.00	
WorléeAdd 429		1.50	
OS-Cobalt 6		0.35	(Borchers)
OS-Calcium 10		0.55	(Borchers)
OS-Zirconium 12		0.45	(Borchers)
Borchi Nox M2		0.50	(Borchers)
		<u>100.00</u>	

Non volatile content: approx. 78.5%
 Density, 20 °C: approx. 1.35 g/cm³
VOC - content: approx. 290 g/l

Worlée - Chemie G.m.b.H.
 ATA - 1 -
 Revision: March 2009