

Starting Point Formulation No. 1.5238 - 08

Undercoat lacquer, white
VOC < 300 g/l (2010)
Category A / d

WorléeKyd SD 7003	85% in dearomat. HC 160-200	20.00
WorléeThix 670 hs	70% in dearomat. HC 160-200	5.00
Disperbyk 107		0.20 (Byk)
Kronos 2315		23.00 (Kronos)
Heladol 30		32.50 (Herbert Lange)
Sipernat 820 A		6.00 (Degussa)
Dearomat. HC 160-200		11.78
OS-Cobalt 6		0.17 (Borchers)
OS-Calcium 10		0.35 (Borchers)
OS-Zirconium 12		0.50 (Borchers)
Borchi Nox M2		0.50 (Borchers)
		<u>100.00</u>

Non volatile content: approx. 82.0%
 Density, 20 °C approx. 1.60 g/cm³
VOC - content: approx. 290 g/l

Worlée - Chemie G.m.b.H.
 ATA - 1 -
 Revision: February 2009